AM POLYMERS GmbH
Hanns-Martin-Schleyer-Str. 9e
D-47877 Willich
Deutschland/ Germany
Email: info@am-polymers.de
Tel.: +49 (0)2154 50 292 10
Fax: +49 (0) 2154 50 292 08

AM Polymers

ROLASERIT® PP01/ PP01GR/ PP03/ PP03GR/ PP05/ PP05GR: Chemical resitance

Testing period		24 hours	1 week	1 month	3 months
Chemical	**Concentration**				
Aceton	100%	++	++	++	++
Benzin		--	--	--	--
Bremsflüssigkeit		++	++	++	++
Decalin		--	--	--	--
Diesel		+	-	-	--
Ethanol	99,9%	++	++	++	++
Frostschutzmittel		++	++	++	++
Glykol	100%	++	++	++	++
Isopropanol	100%	++	++	++	++
Kalilauge	50%	++	++	++	++
Motoröl		++	++	++	++
Natriumcarbonat (Soda)		++	++	++	++
Natronlauge	50%	++	++	++	++
Salzsäure	10%	++	++	++	++
Schwefelsäure	10%	++	++	++	++
Terpentinersatz		--	--	--	--
Toluol	100%	--	--	--	--
Wasser		++	++	++	++
Xylol	100%	--	--	--	--

Legend	
resistant	++
almost resistant	+
Poorly resistant	-
Not resistant	--

©2021 AM POLYMERS GmbH, all rights reserved: This copyrighted document is the property of AM POLYMERS GmbH and is disclosed in confidence. It may not be copied, disclosed to others, or used for manufacturing, without the prior written consent of AM POLMYERS GmbH.